



SPECIFICATION SHEET

UHMW – PE OK 1000

antistatic carbon black No. 931

FDA-Compliant 21 CFR 178.3297

Characteristics and standard values

Properties	Method	SI Unit	SI Value
Density	ASTM D792	g/cc	0.95
	ISO 1183-A	g/cm ³	0.95
Abrasion – Internal method acc. to (Slurry-test rel. to GUR4120=100%)	DIN 58836	%	110 – 120
Tensile strength, yield	ASTM D638	psi	2200 – 2900
	ISO 527	MPa	15 – 20
Break elongation	ASTM D638	%	>200
	ISO 527	%	>50
Creep properties under varying compressive stress : Creep <10% in 7 days – (20°C)	max.	psi	1450
		MPa	10
Coefficient of friction, ASTM 1894 metal= Rz 2,5 μ, Pm= 2 N/mm ² , V= 150 mm/min	Static	μ	0.17
	Dynamic	μ	0.12
Shore-hardness, 3-s-value 6mm plate	ASTM D2240	D	63
	ISO 868	D	63
Water absorption		%	< 0.1 (Nil)
Thermal Properties			
Melt temperature	ASTM 3417 ISO 3146	°F	275 - 278
		°C	135 - 137
Permanent operation temp., max.		°F	176
		°C	80
Coefficient of linear expansion	ASTM D696 DIN 53752	73 – 176 °F	≈ 1.1x10 ⁻⁴ /°F
		23 – 80°C	≈ 2.0x10 ⁻⁴ /°C
Electrical Properties			
Volume resistivity	ASTM D257 IEC 93	Ohm-cm	< 10 ⁹
		Ω*cm	< 10 ⁹

The above data are based on the present knowledge and are given without guarantee.
Existing laws and conditions are to be respected by the user of our products.

TSE-OKULEN Americas, L.L.C.

sheet and finished products

4370 112th Terrace North, Clearwater, Florida 33762
www.TSE-OK.com E-mail: info@TSE-OK.com

A Joint Venture of TSE Industries, Inc., Clearwater, Florida (USA) and Ottensteiner Kunststoff GmbH & Co. KG (Germany).