



SPECIFICATION SHEET

UHMW – PE OK 1000 - R90

MULTICOLOR - REPROCESSED

Characteristics and standard values

Properties	Method	SI Unit	SI Value
Density	ASTM D792 ISO 1183-A	g/cc g/cm ³	0.94 0.94
Abrasion – Internal method acc. to (Slurry-test rel. to GUR4120=100%)	DIN 58836	%	145
Tensile strength, yield	ASTM D638 ISO 527	psi MPa	2000 – 2500 14 – 17
Break elongation	ASTM D638 ISO 527	% %	50 – 300 >50
Creep properties under varying compressive stress : Creep <10% in 7 days – (20°C)	max.	psi MPa	1450 10
Coefficient of friction, ASTM 1894 metal= Rz 2,5 μ, Pm= 2 N/mm ² , V= 150 mm/min	Static	μ	0.20
	Dynamic	μ	0.15
Shore-hardness, 3-s-value 6mm plate	ASTM D2240	D	63
	ISO 868	D	63
Water absorption		%	< 0.1 (Nil)
Thermal Properties			
Melt temperature	ASTM 3417	°F	275 - 278
	ISO 3146	°C	135 - 137
Permanent operation temp., max.		°F	176
		°C	80
Coefficient of linear expansion	ASTM D696	73 – 176 °F	≈ 1.1x10 ⁻⁴ /°F
	DIN 53752	23 – 80°C	≈ 2.0x10 ⁻⁴ /°C
Electrical Properties			
Volume resistivity	ASTM D257	Ohm-cm	< 10 ¹⁴
	IEC 93	Ω*cm	< 10 ¹⁴

The above data are based on the present knowledge and are given without guarantee.
Existing laws and conditions are to be respected by the user of our products.

TSE-OKULEN Americas, L.L.C.

sheet and finished products

4370 112th Terrace North, Clearwater, Florida 33762
www.TSE-OK.com E-mail: info@TSE-OK.com

A Joint Venture of TSE Industries, Inc., Clearwater, Florida (USA) and Ottensteiner Kunststoff GmbH & Co. KG (Germany).